# SOFT-SHIELD® 2000

# Knitted Yarn Over Foam Core EMI Shielding Gaskets



Value Customer **Proposition:** SOFT-SHIELD® 2000 gaskets consist of silver-plated nylon yarn knitted over a highly compressible, thermoplastic EPDM foam core. Through a special treatment process, the yarn jacket is secured to the core. This self terminating outer layer eliminates the need for secondary termination efforts and metal particle debris associated with the cut ends of common wire mesh gaskets. SOFT-SHIELD 2000 gaskets are designed specifically for EMI shielding electronic enclosures where weather sealing is not a requirement. The low closure force characteristic of SOFT-SHIELD 2000 gaskets allows enclosures to be designed with fewer fasteners and/or thinner panels.

## Configurations:

Standard SOFT-SHIELD 2000 gaskets include both rectangular and D cross sections. Gaskets are provided in bulk on spools or cut to specified lengths. For attachment to flanges or other mounting surfaces, these gaskets are available with an acrylic pressure-sensitive adhesive (PSA) option for quick, efficient application. Gaskets can also be produced as 4-corner spliced picture frames.

#### **Contact Information:**

Parker Hannifin Corporation
Chomerics Division
77 Dragon Court
Woburn, MA 01801

phone 781 935 4850 fax 781 933 4318 chomailbox@parker.com

www.parker.com/chomerics



#### **Product Features:**

- ~70 dB attenuation from 20 MHz to 10 GHz
- ~1 lb/inch (0.175 N/mm) closure force
- No degradation in performance after 10,000 compression cycles
- Self-terminating with no secondary operations
- <25% compression set at 50% deflection, 22 hr. at 158°F (70°C)

- Operating temperature of -50° F to 158° F (-46° C to 70° C)
- Broad compression range of  $35\% \pm 20\%$ .
- Continuous lengths on reels, cut-to-length
- UL 94HB flammability rated



### SOFT-SHIELD® 2000 - Available Profiles

#### **ORDERING INFORMATION**

Use the following part numbers to order



Table 1 - Profiles inches (mm)

Height	Width	Profile	Shape	Cross Section Tolerances	Cut-To-Length
0.130 (3.30)	0.190 (4.82)	6789	Rect.	±0.040 ( ±1.01)	
0.200 (5.08)	0.200 (5.08)	6790	Square	±0.040 ( ±1.01)	
0.250 (6.35)	0.250 (6.35)	6791	Square	±0.040 ( ±1.01)	
0.130 (3.30)	0.250 (6.35)	6794	Rect.	±0.040 ( ±1.01)	Up to 10.000' ±0.060 (127-254 ±1.52)
0.375 (9.53)	0.375 (9.53)	6793	Square	±0.060 ( ±1.52)	
0.140 (3.56)	0.500 (12.70)	6795	Rect.	±0.050 ( ±1.27)	Over 10.000' add ±0.060 (254 ±1.52) for every 10"
0.250 (6.35)	0.500 (12.70)	6797	Rect.	±0.060 ( ±1.52)	Tot every to
0.375 (9.53)	0.500 (12.70)	6902	D	±0.060 ( ±1.52)	
0.100 (2.54)	0.140 (3.56)	6903	D	±0.040 ( ±1.01)	
0.250 (6.35)	0.375 (9.53)	6792	D	±0.040 ( ±1.01)	

Figure 1 Typical Compression-Deflection





Figure 2 Typical Shielding Effectiveness



www.parker.com/chomerics

CHOMERICS and SOFT-SHIELD are registered trademarks of Parker Hannifin Corporation. ® 2018

TB 1092 EN November 2018

